

RockMax[®] High Performance Linerboard

WestRock RockMax Linerboard is specified to meet demanding strength requirements for greater flexibility in designing ECT Packaging.

- Optimized for production of high performance packaging structures.
- ISO certified mills.
- These grades are produced to compression standards and do not have upper or lower basis weight limits.

	31	33
Grade Code	KL31RX	KL33RX
SCT-CD (STFI), lb_r/in Tappi T 826		
Target*	21.0	22.5
Reject Below	18.4	20.0
Moisture Content, % Tappi T 412		
Average (%)	7.5	7.5
Range (+/-)	1.5	1.5
Porosity (Gurley), sec/100cc Tappi T 460		
Reject Below	12	12
Internal Bond, ft-lb/in² Tappi T 569		
Scott Bond - Reject Below	75	75
Slide Angle (Degrees) Tappi T 815		
Reject Below	18	18
Cobb 2 Minute (TOP), g/m² Tappi T 441		
Reject Above	75	75
Reject Below	30	30

*Target - Target is a long term average and not a roll or order based guarantee.